

EMC LABS, INC.

9830 S. 51st Street, Suite B109, Phoenix, AZ 85044
Phone: 800-362-3373 or 480-940-5294 - Fax: (480) 893-1726

Laboratory Report
0193623

Bulk Asbestos Analysis by Polarized Light Microscopy


NVLAP#101926-0

Client:	NORTH WEST RESTORATION	Job# / P.O. #:	
Address:	1837 TERMINAL DR.	Date Received:	10/27/2017
	RICHLAND WA 99354	Date Analyzed:	10/27/2017
Collected:	10/26/2017	Date Reported:	10/27/2017
Project Name:	092417(b) (6)	EPA Method:	EPA 600/R-93/116
Address:		Submitted By:	TODD LEE
		Collected By:	

Lab ID Client ID	Sample Location	Layer Name / Sample Description	Asbestos Detected	Asbestos Type (%)	Non-Asbestos Constituents
0193623-001 092417	INERT WASTE DUMP/WATER MAIN LINE	Transite, Beige/ Gray	Yes	Chrysotile 15%	Quartz Carbonates Gypsum Binder/Filler 85%



Analyst - Kurt Kettler



Signatory - Lab Manager - Ken Scheske

Distinctly stratified, easily separable layers of samples are analyzed as subsamples of the whole and are reported separately for each discernible layer. All analyses are derived from calibrated visual estimate and measured in area percent unless otherwise noted. The report applies to the standards or procedures identified and to the sample(s) tested. The test results are not necessarily indicative or representative of the qualities of the lot from which the sample was taken or of apparently identical or similar products, nor do they represent an ongoing quality assurance program unless so noted. These reports are for the exclusive use of the addressed client and that they will not be reproduced wholly or in part for advertising or other purposes over our signature or in connection with our name without special written permission. The report shall not be reproduced except in full, without written approval by our laboratory. The samples not destroyed in testing are retained a maximum of thirty days. The laboratory measurement of uncertainty for the test method is approximately less than 1 by area percent. Accredited by the National Institute of Standards and Technology, Voluntary Laboratory Accreditation Program for selected test method for asbestos. The accreditation or any reports generated by this laboratory in no way constitutes or implies product certification, approval, or endorsement by the National Institute of Standards and Technology. The report must not be used by the client to claim product certification, approval, or endorsement by NVLAP, NIST, or any agency of the Federal Government. Polarized Light Microscopy may not be consistently reliable in detecting asbestos in floor coverings and similar non-friable organically bound materials.